

Specification for Li-ion Rechargeable cylindrical battery

圆柱锂离子电池 规格书

MODEL/型号:
INR 18650 3000mAh(30EF)

Prepared By/Date 编制/日期	Checked By/Date 审核/日期	Approved By/Date 批准/日期
} 长兴	吴 夏 红	刘 毅 斌

	Signature 签字	Date 日期
	Customer Approval 客户承认	Company Name: 公司名称(印章)

1.0 Scope 适用范围


This document describes the Product Specification of the Lithium-ion rechargeable battery cell supplied by Shenzhen Fest Technology Co., Ltd.

本规格说明书描述了深圳费思特科技有限公司的可充电锂离子电芯的产品性能指标。



2.0 Specifications 基本规格

Items 项目	Specifications 规格
2.1 Model 型号	INR18650-3000 (30EF)
2.2 Min. Capacity 最小容量	2950mAh Charge: 0.5C, 4.20V, CCCV 60mA cut-off, Discharge: 0.2C, 2.5V discharge cut-off
2.3 Nominal Voltage 额定电压	3.7V
2.4 Max. Charge Voltage 最大充电电压	4.20 V
2.5 Discharge Cut-off Voltage 放电截至电压	2.50V
2.6 Standard charge 标准充电	CCCV, 1.50A, 4.20 ±0.05 V, 60mA cut-off
2.7 Max. Charge Current 最大充电电流	CCCV, 3A, 4.20 ±0.05 V, 60mA cut-off
2.8 Max. Continuous Discharge Current 最大持续放电电流	15 A
2.9 Max. Pulse Discharge Current 最大瞬间放电电流	30A (2s pulse)
2.10 Max. Diameter 电池直径	≤18.40 mm
2.11 Max. Height 电池高度	≤65.50mm
2.12 Weight 电池重量	≤ 48. 0g
2.13 Impedance 内阻	≤ 18 mΩ
2.14 Operating temperature (surface temperature) 使用时电芯表面温度	Charge 充电: 0°C~50°C
	Discharge 放电: -20°C~75°C
	Storage 贮存: -20°C~45°C

3.0 Configuration 外形示意图



4.0 Mainly capability graph (For Reference Only) 主要放电曲线 (仅供参考)



5.0 Characteristic 电池性能

a. Environmental conditions 测试环境

Unless otherwise specified, all tests stated in this specification are conducted at temperature 23 ± 3 ° and humidity under 65%. 若没有特别说明, 电池均在环境温度 $23^{\circ}\text{C} \pm 3^{\circ}\text{C}$, 相对湿度小于 65% 的条件下进行测试。

b. Measuring equipment 测试设备

(1) Amp-meter and volt-meter 容量电压测试

The amp-meter and volt-meter should have an accuracy of the grade 0.5mA and mV or higher. 容量电压测试设备的精度需达到 0.5mV/mA 以上。

(2) Slide caliper 尺寸测试

The slide caliper should have 0.01 mm scale. 测量尺寸时量具需达 0.01 mm 以上精度。

(3) Impedance meter 内阻测试

The impedance meter with AC 1kHz should be used. 内阻测试在 AC 1kHz 的条件下进行。

c. Standard charge 标准充电

charging the cell CCCV with charge current 0.5C, constant voltage 4.2V and 60mA cut-off in CV mode at 23°C for capacity. 充电电流为 0.5C, 当电池端电压达到 4.2V 时, 改为恒压充电, 充电电流小于 60mA 时停止充电。

d. Standard discharge capacity 标准放电

discharge current of 600mA(0.2C) with 2.5V cut-off at 23°C within 1hour after the standard charge.

标准充电搁置 1h 后, 在 23°C 温度下, 以 0.2C 电流放电至 2.50V 的容量。

5.1 Electrical Characteristic 电化学性能

序号 NO.	项目 Item	标准 Standard	测试方法 Test Method
1	Discharge rate capabilities 放电倍率性能	$0.2\text{C} \geq 2950\text{mAh}$ $0.5\text{C} \geq 2900\text{mAh}$ $1.0\text{C} \geq 2850\text{mAh}$ $3.0\text{C} \geq 2800\text{mAh}$ $5.0\text{C} \geq 2700\text{mAh}$	Standard charged, then rest for 30mins and discharge at 0.2C、0.5C、1C、3C、5 C and 2.5V cut-off 电池标准充电后搁置 30mins, 分别以 0.2C、0.5C、1C、3C、5 C 进行放电至 2.5V 截止
2	capacity retention and recovery 容量保持及恢复能力	Residual capacity $\geq 94\%$ Recoverable capacity $\geq 98\%$ 剩余容量 $\geq 94\%$ 恢复容量 $\geq 98\%$	Standard charged under the condition of normal atmospheric pressure and the environmental temperature of $23^{\circ}\text{C} \pm 3^{\circ}\text{C}$, Stored for 28 days, then discharge at 0.2 C to 2.75V measuring residual capacity; Then standard charge/discharge measure recoverable capacity. 测量电池的初始状态和初始容量, 电池标准充电后, 在环境温度 $23^{\circ}\text{C} \pm 3^{\circ}\text{C}$ 下开路放置 28 天, 0.2 C 放电至 2.75V, 测量电池的剩余容量; 然后标准充放电测试电池的恢复容量。

3	Low Temperature Performance 低温性能	discharge capacity ≥85% rated capacity no distortion and no rupture 放电容量≥85% 额定容量	The cell shall be charged in accordance with the standard charge. Then stored in the temperature of -10°C±1 °C for 4h, Discharge at the constant current of 0.2C down to the end-of-discharge voltage 2.750V. 按标准充电方法充电后，放入-10°C±1°C低温箱中恒温4h，在此条件下 0.2C 放电至 2.750V。
4	Cycle Life 循环寿命	3A 充/10A 放电循环 ≥300cycles	3A charged the cell to 4.2V, then change to charge with constant voltage till the current less than or equal to 60mA, rest for 30mins; 10A discharge to 2.75V, one cycle is finished, rest for 30mins. Then repeat above steps, when capacity is less than 70% of initial capacity, the battery life is over. 测试条件： 3A 恒流充电至 4.2V，然后恒压至电流减小到 60mA 截止充电，搁置 30min；10A 放电到 2.75V，完成一个循环，搁置 30mins。重复上述步骤。当放电容量小于 70% 标称容量，寿命终止。

5.2 Safety Characteristic 安全性能

NO. 序号	Item 项目	Standard 标准	Test Method 测试方法
1	Overcharge 过充性能	No fire、No explosion 不起火、不爆炸	After standard charge, rest for 10mins; then charge at constant current of 3C to 10V.(or charge at 3C for 90mins). 按标准充电后，搁置 10mins；3C 恒流充电至电压 10V。（或 3C 充电 90mins） ---UL1642
2	Forced discharge 强制放电	No fire、No explosion 不起火、不爆炸	The battery to be discharged with standard discharging condition, Inverse charge current =1C; time: ≥90mins 按标准放电要求对电池放电，以1C反向充电，充电时间不低于 90mins。 ---UL1642

3	Short Circuit test 短路性能	No fire No explosion 不起火、不爆炸	The battery to be fully charged with standard charging condition, and short the positive and negative terminals with wire resistance $\leq 50\text{m}\Omega$. Tests are to be conducted at $23^{\circ}\text{C} \pm 3^{\circ}\text{C}$ and at $55^{\circ}\text{C} \pm 5^{\circ}\text{C}$, keep 24h or case temperature decline to 20% of the max temperature, test is over. 充满电的电池分别置于 $23^{\circ}\text{C} \pm 3^{\circ}\text{C}$ 和 $55^{\circ}\text{C} \pm 5^{\circ}\text{C}$ 环境下, 用外部电阻不高于 $50\text{m}\Omega$ 的电阻将每只电池短路。持续 24h 或外壳温度下降至最高温度的 20% 时, 结束试验。 ---UL1642
4	Crush test 挤压实验	No fire、No explosion 不起火、不爆炸	A battery is crushed between two flat surfaces. The applied force is $13\text{ kN} \pm 1\text{ kN}$ by hydrocylinder, Once the maximum pressure has been obtained or voltage decrease to 1/3 of nominal voltage sharply, then release pressure. 电池在两个平面间承受挤压, 由液压油缸施加 $13\text{ kN} \pm 1\text{ kN}$ 的挤压力。一旦挤压力达到最大或电池电压锐减到电池电压的三分之一, 卸压。 ---UL1642
5	Shock test 冲击测试	No fire、No explosion 不起火、不爆炸	The full charged battery is fixed on shock table, to force a certain shock to three mutual vertical direction, in initial 3ms, the min. average acceleration is 75gn, the peak acceleration is between 125gn and 175gn. 充满电的电池被固定在冲击台上, 在三个互相垂直轴的方向各承受一次等值的冲击。初始 3ms 内, 最小平均加速度为 75gn, 峰值加速度在 125gn 和 175gn 间。 ---UL1642
6	Heating test (130 °C) 热滥用测试	No fire、No explosion 不起火、不爆炸	The cells are fully charged with standard charging condition, and put into incubator with nature air or cycled air convected, heat battery by velocity of $5^{\circ}\text{C} \pm 2^{\circ}\text{C}/\text{min}$ to $130^{\circ}\text{C} \pm 2^{\circ}\text{C}$, and maintain for 10mins. 电池按标准充满电后放于自然或循环空气对流的恒温箱中, 温度以 $5^{\circ}\text{C}/\text{min} \pm 2^{\circ}\text{C}$ 的速率升至 $130^{\circ}\text{C} \pm 2^{\circ}\text{C}$ 并保持 10mins。 ---UL1642
7	Temperature Cycling Test 温度循环试验	no leakage, no fire, no explosion 不泄漏, 不起火、不爆炸	The fully charged batteries are placed in a test chamber and subjected to the following cycles: a) Raising the temperature to $75^{\circ}\text{C} \pm 2^{\circ}\text{C}$ within 30 minutes and maintaining this temperature for 6 hours. b) Reducing the temperature to minus $40^{\circ}\text{C} \pm 2^{\circ}\text{C}$ within 30 minutes and maintaining this temperature for 6 hours. c) Repeating the sequence for a further 9 cycles. d) After the 10th cycle, storing the batteries for 24 hours prior to

			<p>examination.</p> <p>充满电的电池: 75° C±2° C 搁置 6h; -40° C±2° C 搁置 6h, 两个极端温度之间最大间隔时间为 30 分钟。循环 10 次后将电池搁置 24 小时进行检测。</p> <p>---UN38.3</p>
--	--	--	---

5.3 Environment Adaptation Performance 环境适应性性能

NO. 序号	Item 项目	Standard 标准	Test Method 测试方法
1	Altitude/Low pressure simulation test 高空低压模拟测试	no leakage, no fire, no explosion 不泄漏, 不起火、不爆炸	The full charged cells are to be stored for 6h at an vacuum environment with pressure of less than 11.6kPa and a temperature of 23°C ± 3°C. 将充满电的电池在 23°C ± 3°C、大气压 ≤ 11.6 kPa 的真空中储存 6h。 ---UN38.3
2	Free drop test 自由跌落试验	no fire, no explosion 不起火, 不爆炸	The fully charged battery drops on the concrete ground from height(1m), total 3 times, to obtain the shock of random directions. 充满电的电池三次从 1m 高的地方跌落到混凝土地面, 以此获得随机方向的冲击。 ---UL1642
3	Vibration test 振动试验	No remarkable damage、No smoking、No explosion 电池外观无明显损伤、不泄漏、不冒烟、不爆炸	After standard charging, fixed the cell to vibration table and subjected to vibration cycling that the frequency is to be varied at the rate of 1Hz per minute between 10Hz and 55Hz, the excursion of the vibration is 1.52mm. The cell shall be vibrated for 90 minutes per axis of x, y axes. 将充满电的电池以振幅 0.76mm (双振幅为 1.52mm) 的正弦振动, 振动频率范围为 10Hz~55Hz, 频率变化速率 1Hz/min。沿 X、Y、Z 三个方向振动, 每个方向振动 90mins ± 5mins。 ---UL1642

5.4 Storage Temperature for Shipping 运输过程存储温度

If the cell is kept as ex-factory status (50% of charge), the 0.2C recoverable capacity rate is more than 90%.

1 month	1 个月	-20 ℃ ~ 60 ℃
2 months	2 个月	-20 ℃ ~ 40 ℃
3 months	3 个月	-20 ℃ ~ 25 ℃

5.5 appearance 外观


There shall be no such defect as deep scratch, flaw, crack, rust, leakage, which may adversely affect commercial value of the cell.

电芯外观不存在明显的刮痕、凹坑、裂痕、锈蚀、漏液等影响电芯性能的外观不良。

6.0 Package 包装

The cells are packed with Shenzhen Fest Technology Co., Ltd. standard carton box, which hold four inner boxes. There are 100pcs 18650 cells per inner box. And the inner box and outer box identifies battery capacity, voltage and impedance information.

电芯使用深圳费思特科技有限公司标准的包装方式, 每箱有 4 盒, 每盒 100pcs. 内盒及外箱均标识电池容量、电压及内阻范围等信息。



7.0 Warranty Period & Product Liability 保质期及产品责任

Warranty period of this product is 12 months from manufacturing code. Shenzhen Fest Technology Co., Ltd. is not responsible for the troubles caused by mishandling of the battery which is against the instructions in this specification.

保质期是从出厂日期（喷码）开始起 12 个月；深圳费思特科技有限公司对因没有按本规格书规定操作而导致的意外不负责任。

8.0 Warnings and Cautions in Using the Battery 电池使用警告及注意事项

To prevent a possibility of the battery from leaking, heating or explosion please observe the following precautions:

为防止电池可能发生泄漏,发热、爆炸,请注意以下预防措施:

- When using a new battery for the first time or after long term storage, please use the battery charger specifically for that purpose fully charge the battery before use.
在使用新电池前, 或者长期存放后第一次使用电池, 在使用前请使用专用充电器将电池充满电。
- Do not disassemble or open, crush, bend or deform, puncture, or shred;
请勿拆解或打开、挤压、弯折、变形、刺穿、敲碎;
- Do not modify or remanufacture, attempt to insert foreign objects into the battery, immerse or expose to water or other liquids such as water, seawater, drinks such as soft drinks, juices, coffee or others, or expose to fire, explosion, or other hazard.
请勿修改或改装, 不要试图将外物插入电池, 不要浸入或暴露在水或其它液体中如淡水、海水、饮料(果汁、咖啡等), 远离火源、爆炸物和其他危险;
- Do not short circuit a battery or allow metallic or conductive objects to contact the battery terminals.
请勿使电池短路, 也不要让金属或其它导体接触电池接电端子;
- Avoid dropping the phone or battery. If the phone or battery is dropped, especially on a hard surface, and the user suspects damage, take it to a service center for inspection.
不要跌落主机或电池, 如果主机或电池不慎跌落(尤其在硬表面上), 用户怀疑电池损坏, 则应找服务中心检查;
- The battery replacement shall be done only by either cells supplier or device supplier and never be done by the user.
更换电芯应由电芯供应商或设备供应商完成, 用户不得自行更换。
- Replace the battery only with another battery that has been qualified with the system per standard. Use of an unqualified battery may present a risk of fire, explosion, leakage, or other hazard.
更换电池时只能使用通过标准认证的电池, 使用未经认证的电池可能存在起火、爆炸、或其它危险;
- Don't keep a battery at rest for a long time (over 6 months). Safety accident may happen when recharging battery which has a rest for a long time.
避免电池长时间放置不用, 长期放置不用的电池重新充电时可能会发生安全问题。

- In the event of a battery leak, do not allow the liquid to come in contact with the skin or eyes. If contact has been made, wash the affected area with large amounts of water and seek medical advice.
如果电池发生漏液，不要让电池接触皮肤和眼睛，如果接触不幸发生，则用大量的水冲洗接触部位或寻求医生帮助；
- Battery usage by children should be supervised. Seek medical advice immediately if a battery has been swallowed
儿童使用电池应受到监督；如果电池被吞食了，立即就医；
- Never disassemble cells. The disassembling may generate internal short circuit in the cell, which may cause firing or other problems.
在任何情况下不得拆卸电芯。拆卸电芯可能会导致内部短路，进而引起着火及其它问题。
- Never incinerate nor dispose the cells in fire. These may cause firing of the cells, which is very dangerous and is prohibited.
在任何情况下，不得燃烧电芯或将电芯投入火中，否则会引起电芯燃烧，这是非常危险的，应绝对禁止。
- When use the battery , must to ensure the charge and discharge voltage of the battery is between 2.75V to 4.2V.
使用电池时需保证每个电池的充放电上下限电压在 4.2V 至 2.75V 之间。
- Do not remove the outer sleeve from a battery pack nor cut into its housing.
不要把电池（电池组）的外套去除。
- Do not mix our batteries with other battery brands or batteries of a different chemistry such as alkaline and zinc carbon.
不要将我公司司电池与其他品牌的电池或者不同种类的电池，比如碱性锌电池混用。
- Do not mix new batteries in use with semi-used batteries, over-discharge may occur.
不要将新旧电池混用,可能会导致过放电。
- Promptly dispose of used batteries in accordance with local regulations.
按当地法规迅速处理报废电池；

8.1 ship 运输

The cells might be damaged during shipping by shock. If any abnormal features of the cells are found such as deformation of the cell package, smelling of an electrolyte, an electrolyte leakage and others, the cells shall never be used any more. The Cells with a smell of the electrolyte or a leakage shall be placed away from fire to avoid firing.

电芯在运输过程中可能因撞击等原因而损坏，若发现电芯有任何异常特征，如外壳破损，闻到电解液气味，电解液泄漏等，该电芯不得使用。有电解液泄漏或闻到异常味道的电池应远离火源以避免着火。

8.2 Storage 贮存

The cell shall be stored at the environmental condition of -20°C - 45°C and $65\% \pm 20\%$ RH. The voltage for long time storage shall be 3.5V-3.7V range. If the cell has to be stored for a long time (Over 3 months), the environmental condition should be: Temperature: $23^{\circ}\text{C} \pm 3^{\circ}\text{C}$ Humidity: $65\% \pm 20\%$ RH; please activate the battery once every 3 months according to the following method: Charge with current 0.2C until the voltage achieve to 3.7V.

电芯储存温度必须在 -20°C ~ 45°C 的范围内。长期存储电池（超过 3 个月）须置于温度为 $23^{\circ}\text{C} \pm 3^{\circ}\text{C}$ 、湿度为 $65\% \pm 20\%$ RH 的环境中。长期贮存电压为 3.5V~3.7V。保质期内每隔 3 个月对电池用 0.2C 电流进行补充电，至电压达到 3.7V。

深圳费思特科技有限公司

Shenzhen Fest Technology CO., Ltd.

地址：深圳市宝安区龙华沙吓宝山工业区 M&E 栋

Add: M&E Building, BaoShan Industrial Park, MingTian Road, Shaxia, longhua, Bao'an District, Shenzhen, China

电话 Tel: +86 755 89304183

传真 Fax: +86 755 27764602

网址 Website: www.efestpower.com